

### Color vs. Material Reference Guide

Color Description, Name	Ref. #	Steel Gauge				Aluminum Gauge					Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)
		29	24	22	26	0.032	0.040	0.050	0.063	0.080			
<b>Standard Colors</b>													
Classic Bronze	1	*	*	*	*	*	*	*	*	*	0.118	0.83	5
Black	2	*	*	*	*	*	*	*	*	*	0.047	0.86	-2
Medium Bronze	3	*	*	*	*	*	*	*	*	*	0.326	0.86	34
Chocolate Brown	4	*	*	*	*	*	*	*	*	*	0.259	0.86	24
Concord Cream	5	*	*	*	*	*	*	*	*	*	0.65	0.85	78
Sandstone	6	*	*	*	*	*	*	*	*	*	0.57	0.85	66
Redwood	7	*	*	*	*	*	*	*	*	*	0.22	0.83	18
Mission Red	8	*	*	*	*	*	*	*	*	*	0.413	0.86	45
Sierra Tan	9	*	*	*	*	*	*	*	*	*	0.481	0.86	54
Ascot White	10	*	*	*	*	*	*	*	*	*	0.693	0.86	83
Forest Green	11	*	*	*	*	*	*	*	*	*	0.277	0.85	27
Patina Green	12	*	*	*	*	*	*	*	*	*	0.457	0.86	51
Dove Grey	13	*	*	*	*	*	*	*	*	*	0.35	0.83	36
Siam Blue	14	*	*	*	*	*	*	*	*	*	0.34	0.85	35
Rawhide	15	*	*	*	*	*	*	*	*	*	0.55	0.85	64
Rocky Grey	16	*	*	*	*	*	*	*	*	*	0.285	0.86	28
Regal Blue	18	*	*	*	*	*	*	*	*	*	0.268	0.84	23
Teal	19	*	*	*	*	*	*	*	*	*	0.3	0.85	30
Slate Grey	20	*	*	*	*	*	*	*	*	*	0.35	0.83	36
Slate Blue	21	*	*	*	*	*	*	*	*	*	0.31	0.86	31
Boysenberry	25	*	*	*	*	*	*	*	*	*	0.282	0.86	27
Bone White	26	*	*	*	*	*	*	*	*	*	0.74	0.86	90
Hartford Green	27	*	*	*	*	*	*	*	*	*	0.25	0.85	23
Hemlock Green	30	*	*	*	*	*	*	*	*	*	0.3	0.86	30
Charcoal Grey	62	*	*	*	*	*	*	*	*	*	0.3	0.83	29
55% Al-Zn Alloy Coated Steel with Acrylic Coating	97	*	*	*	*	*	*	*	*	*	0.68	0.14	58
Mill Finish- Aluminum	99										-	-	-
<b>Matte Finish</b>													
Char Brown	29	*	*	*	*	*	*	*	*	*	0.35	0.89	38
Matte Black	32	*	*	*	*	*	*	*	*	*	0.093	0.84	2.4
Ash Grey	33	*	*	*	*	*	*	*	*	*	0.055	0.86	63.93
Thunder Grey	34	*	*	*	*	*	*	*	*	*	0.32	0.86	32.32
Almond	36	*	*	*	*	*	*	*	*	*	0.64	0.86	76.47
Anchor Grey	37	*	*	*	*	*	*	*	*	*	0.392	0.84	41.7
<b>Premium Finish</b>													
Brite Red	17	*	*	*	*	*	*	*	*	*	0.37	0.86	39
Coppertone	23	*	*	*	*	*	*	*	*	*	0.5	0.86	57
Antique Patina	24	*	*	*	*	*	*	*	*	*	0.26	0.86	25
Silversmith	28	*	*	*	*	*	*	*	*	*	0.47	0.81	51
Champagne	31	*	*	*	*	*	*	*	*	*	0.55	0.79	62
Titanium	35	*	*	*	*	*	*	*	*	*	0.51	0.87	59
Clear Satin Anodized	70	*	*	*	*	*	*	*	*	*	0.77	0.7	92
Dark Bronze Anodized	71	*	*	*	*	*	*	*	*	*	0.15	0.77	6
<b>Advanta Americana Classic (stamped shingles)</b>													
Asheland Slate	AS	*	*	*	*	*	*	*	*	*	0.44	0.83	48
Baja Slate	BS	*	*	*	*	*	*	*	*	*	0.27	0.83	25
Beech Tree	BT	*	*	*	*	*	*	*	*	*	0.38	0.84	40
Deep Granite	DG	*	*	*	*	*	*	*	*	*	0.25	0.83	22
Quarry Slate	QS	*	*	*	*	*	*	*	*	*	0.31	0.84	31
Rocky Cliff	RC	*	*	*	*	*	*	*	*	*	0.29	0.83	27
Shaded Spruce	SS	*	*	*	*	*	*	*	*	*	0.25	0.83	22
Weathered Stone	WN	*	*	*	*	*	*	*	*	*	0.27	0.83	25
Willow Slate	WS	*	*	*	*	*	*	*	*	*	0.3	0.83	29